



Product Data and Technical Information

POLYMER TYPE: POLYPROPYLENE RANDOM COPOLYMER

GRADE NAME : RG 3420L

PACKING : PP bags of 25 kgs, 50 bags on a pallet shrunk by PE

APPLICATION : BOPP Films

PRODUCT FEATURES : Random Copolymer (Ethylene/Propylene)

PROCESSING METHOD : Extrusion

Property	Test Method	Unit	Value
MFR (230° C/ 2.16 Kg)	ASTM D1238/L	gr/10min	6
Tensile Modulus of Elasticity (1mm/min)	ASTM D638	MPa	600
Tensile Strength at Yield (50 mm/min)	ASTM D638	MPa	20
Elongation at Yield(50 mm/min)	ASTM D638	%	15
Notched Izode Impact at 23°	ASTM D256	KJ/m2	15
Vicat Softening Point, 10N	ASTM D1525	°C	120
Rockwell hardness	ASTM D785	R-Scale	60
Melting Point , DSC	ASTM D3417	°C	136
Density	ASTM D792	gr/cm3	0.90

"The information in this publication is submitted without prejudice, and is based on our current knowledge and experience and on a limited number of tests.

In view of the many factors that may affect processing and application, these data do not relieve the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply and legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication."